

Physical Property	Typical Value	Test Method
Appearance	Black thick paste	–
Application Temperature (Ambient)	-20°F to 140°F	–
Consistency	Trowel grade	–
Flash Point	105°F	ASTM D3278
Underwater Adhesion	100%	ASTM D3409
VOC Content (maximum)	250 g/L	EPA Method 24
Weight	8.5–9.5 lbs./gal.	–

APPROVALS AND CERTIFICATIONS

- 100% underwater adhesion per ASTM D3409
- Meets or exceeds ASTM D4586 Standard Specification for Asphalt Roof Cement, Asbestos-Free, Type I, Class II
- Miami-Dade County Approved
- Can contribute to LEED certification credits

DESCRIPTION

EnduraRoof Extreme Rubberized Flashing Cement is a top-tier roof flashing cement designed specifically for professional roofers. **EnduraRoof Extreme Rubberized Flashing Cement** is enhanced with SEBS rubber and features high-quality solvents and UV inhibitors, making it the ideal choice for permanent repairs in all weather conditions, whether wet or dry.

FEATURES

- Formulated with UV inhibitors and SEBS rubber for enhanced durability
- Designed for extreme weather conditions, with an application range of -20°F to 140°F
- Offers superior elasticity and flexibility, making it perfect for control joints, seams, or areas prone to movement

USAGE

Repairs holes, cracks, and splits in composition shingles, mineral surface cap sheets, asphalt roofs, APP, SBS modified rubber roofs, cured concrete, and metal roofs. Seals leaks and gaps around flashings, chimneys, masonry, vents, skylights, metal edging joints, gutters, and more.

SURFACE PREPARATION

Clean dirt, loose material, and any other foreign matter from the surface. Remove embedded gravel and cut away old roof cement to ensure bond. Remove rust and scale with wire brush.

EnduraRoof Extreme Rubberized Flashing Cement

APPLICATION

Apply: For cartridge: cut nozzle at angle, puncture inner seal, and apply with caulking gun.

Work into hole ⅛" to ¼" thick with a trowel, putty knife or gloved hand. Press firmly and spread at least 2" beyond, feathering edges. If hole is over ¼" wide or 2" long, reinforce with **EnduraRoof Polyester Repair Fabric** between two layers of cement.

COVERAGE

Approximately 12 sq. ft. per gallon applied at ⅛" thick.

For 3-course application, approximately 6 sq. ft. per gallon.

CLEAN-UP

Clean tools with kerosene, paint thinner or mineral spirits. Clean hands with waterless hand cleaner.

PACKAGING

3 gallon

PRECAUTIONS

CLOSE AIR INTAKES ON ROOF UNTIL SOLVENTS DISSIPATE! May not yield satisfactory results over some APP torch down membranes. Not for use over coal tar, gravel, rubber or PVC sheet roofing, wood shingles or under APP membrane or other products with burn-off film. To extend repair life, coat with an EnduraRoof roof coating after 30 days.