



TRI-BUILT® 300HT

HIGH TEMPERATURE WATER & ICE PROTECTION

TRI-BUILT® 300HT is a high-tensile-strength rubberized asphalt underlayment specifically designed to withstand temperatures up to 250°F (121°C). Ideal for use under metal including copper, zinc and COR-TEN® (consult technical department for installation instructions), TRI-BUILT® 300HT can also be used under synthetic, concrete and clay tiles and asphalt shingles. This strong, skid-resistant membrane is available in either black or white and provides superior protection from water penetration caused by wind-driven rain and ice dams.

FEATURES AND BENEFITS

- Protects the roof structure from water seepage caused by ice dams and wind-driven rains
- Resists temperatures up to 250°F without degradation of the adhesive
- Seals around roofing nails, staples and screws
- Split-release film provides easier, faster installation
- Resists cracking, drying and rotting, providing long-term waterproofing performance and low lifecycle cost
- Concealed waterproofing system will not detract from the architectural aesthetics of the primary roofing system
- Exposed rubberized asphalt bead along the membrane edge ensures watertightness of lap seams
- 180 days exposure time

STANDARDS

- UL Classified
- ICC-ES ESR #2206
- 2009, 2012, and 2015 International Building Code™
- Meets ASTM D1970
- Miami-Dade County Product Control Approved
- ASTM E108/UL 790 Class A Fire Resistance
- 2016 California Green Building Standards, Title 24
- 2015, 2012, and 2008 ICC 700 National Green Building Standard

STORAGE

TRI-BUILT® 300HT roofing underlayment rolls should be stored on their side, under cover and in areas where the temperature is between 40° and 100°F (4.4° and 38°C). Do not double-stack pallets.

WARRANTY

TRI-BUILT® 300HT products are backed by TRI-BUILT's industry-leading warranty. TRI-BUILT® 300HT Products will display optimal performance when stored under recommended conditions and used within one year of date of manufacture. Please see TRI-BUILT® 300HT TEN YEAR WATERMARK MATERIAL WARRANTY form for complete warranty details. Product installed after one year of date of manufacture is not covered under defect warranty.



TRI-BUILT® 300HT

High Temperature Water & Ice Protection

INSTALLATION

TRI-BUILT® 300HT underlayment is applied when the roof deck is dry and the substrate temperature is 40°F (4.4°C) or higher. At temperatures below 40°F, nailing or priming should be used to temporarily hold the membrane in place while adhesion develops. TRI-BUILT® 300HT is designed to be covered with the primary roofing system and should not be exposed to sunlight for more than 60 days (black film only). White underlayment offers exposure time of 180 days.

Substrate must be free of any moisture. If moisture is present, it may inhibit adhesion. Prepare the roof deck by removing all loose objects, dirt, dust and debris. For re-roofing applications, remove all old materials from the roof deck in the area to be covered with TRI-BUILT® 300HT underlayment. Replace water-damaged sheathing and sweep roof deck thoroughly.

PRIMING

Priming is not required on clean, dry wood, metal or most polyisocyanurate surfaces (polyiso paper facer does require priming). Masonry and exterior gypsum boards (such as DensDeck®) should be primed using an appropriate primer or adhesive. Some rigid insulation boards with porous or dusty surfaces may require priming to promote initial adhesion. Priming is required on all substrates when air or substrate temperatures are below 40°F (4.4°C). Adhesives such as CCW-702, CCW-702WB, CAV-GRIP™ and CCW-AWP are approved for use with TRI-BUILT® 300HT products. Refer to your local building codes to determine acceptable product for use in your region.

Selection of roof deck or insulation substrate and/or use of a primer or adhesive are the responsibility of the architect, specifier or roofing contractor to determine based on the roof assembly and environmental conditions.

VALLEYS, HIPS & RIDGES

Cut TRI-BUILT® 300HT roofing underlayment into manageable lengths. Align over the center of the valley, hip or ridge. Remove release film. Press the middle of the membrane first before working toward the edges. For open valleys, cover TRI-BUILT® 300HT roofing underlayment with metal valley liners.

EAVES & RAKES

Cut TRI-BUILT® 300HT underlayment into 10–15' pieces. Remove 2–3' of release film and align the edge of the membrane, sticky side down, so it overhangs the drip edge by ¾" (10 mm). Continue to remove release film and press as you move across the roof. Use a hand roller and/or hand pressure to press into place. Overlap end laps a minimum of 6". WIP roofing underlayment should reach a point 2' inside the interior wall line. Local codes may require additional courses. If additional courses are required, the top lap must be at least 3½".

DRIP EDGES

At the rake edge, apply TRI-BUILT® 300HT underlayment first and place drip edge on top. At the eave, apply drip edge first and place TRI-BUILT® 300HT underlayment on top of the drip edge so that it overhangs drip edge by ¾" (10 mm).

METAL ROOF UNDERLAYMENT

Under water-shedding metal roof systems or low-slope metal roofs with a minimum ½" slope, start at the low point and apply TRI-BUILT® 300HT over the full surface of the roof deck. Review the metal roofing manufacturer's instructions for limitations and precautions. Beginning at the eaves, apply underlayment from the low point to the high point of the roof, running the roll horizontally.

LAP EDGES

Lap edge seams should be hand rolled to ensure maximum adhesion.

LIMITATIONS

- TRI-BUILT® 300HT should be installed when air, roof deck and membrane temperatures are at or above 40°F (4.4°C).
- TRI-BUILT® 300HT should not be left exposed to sunlight for more than 60 days for black membrane or 180 days for white membrane.
- TRI-BUILT® 300HT membrane should not be folded over the roof edge unless protected by a gutter or other flashing materials.
- The primary roof system must be ventilated to prevent excessive moisture build-up in the interior structure.
- Use caution during the installation of the membrane as it may become slippery when wet or covered with frost.
- TRI-BUILT® 300HT must not to be used in contact with PVC material.
- TRI-BUILT® 300HT is not approved for use in foam set tile applications.
- TRI-BUILT® 300HT is not designed for wall assemblies.

PRODUCT SPECIFICATIONS

PHYSICAL PROPERTIES

Surface	Black/White Engineered Polyolefin Composite Film with Factory-applied Anti-skid Coating	
Membrane	Rubberized Asphalt	

PRODUCT CHARACTERISTIC

UNITS

RESULTS

Roll Length	feet	66
Roll Weight	lbs	55
Roll Size	sq ft	198
Roll Width	inches	36

TYPICAL PERFORMANCE PROPERTIES

TEST METHOD

RESULTS

Thickness	ASTM D1970	40 mils
Low Temperature Flexibility	ASTM D1970	-45°F
Adhesion to Plywood at 75°F	ASTM D1970	35 lbs/ft
Lap Seam Adhesion at 75°F	ASTM D1970	21 lbs/ft
Sealability Around Nail	ASTM D1970	Pass
Slip Resistance	ASTM D1970	Pass
Thermal Stability	ASTM D1970	Pass
Moisture Vapor Permeance	ASTM D1970	0.02 perms
Water Absorption	ASTM D1970	0.5%
Tensile Strength Machine Direction	ASTM D412	250 psi
Tensile Strength Transverse Direction	ASTM D412	1390 psi
Elongation at Break Machine Direction	ASTM D412	250%
Elongation at Break Transverse Direction	ASTM D412	170%

PACKAGING INFORMATION

Boxes (rolls) per pallet		25
--------------------------	--	----

