



TRI-BUILT® HD ISO

High Density Roof Cover Board Insulation

TRI-BUILT® HD ISO is a 1/2" thick high-density polyiso insulation panel specifically designed for use as a cover board. It is manufactured on-line to a premium performance coated glass facer on both sides (CGF). TRI-BUILT HD Coverboard comes standard with light facer on one side of the board and dark on the other. This allows the installer to manage the adhesive flash-off time by choosing between the two different colored facers.

APPLICATIONS

- Constructions requiring FM Class 1 and UL Class A ratings
- Compatible with Single-Ply Roofing Systems (fully adhered and mechanically attached)
- Modified Bitumen Roofing Systems
- Suitable for use with approved fasteners and plates, also cold applied and low-rise adhesives

INSTALLATION

BALLASTED SINGLE-PLY SYSTEMS

Each TRI-BUILT® HD ISO panel should be loosely laid as a coverboard over either an existing roof system or base layers of insulation on the roof deck. Butt edges and stagger joints of adjacent panels. Install the roof cover according to the manufacturer's specifications.

FULLY ADHERED SINGLE-PLY

Each TRI-BUILT® HD ISO panel should be secured as a coverboard over either an existing roof system or base layers of insulation. TRI-BUILT® HD ISO may be adhered to a prepared concrete deck or subsequent layers of insulation with a full mopping of hot steep asphalt, insulation adhesive or cold applied mastic. Butt edges and stagger joints of adjacent panels. Install the roof cover according to the manufacturer's specifications.

RE-ROOFING SINGLE-PLY SYSTEMS

TRI-BUILT® HD ISO provides a singular and sustainable solution in retrofit applications when existing insulation is left in place. To facilitate compliance with ASHRAE 90.1 Standards for energy efficiency, TRI-BUILT® HD ISO can be installed in a single layer on top of intact and dry insulation after the Single Ply membrane is removed. Butt edges and stagger the joints in accordance with good roofing practice and fasten as per manufacturer's specifications. The new Single-Ply membrane can then be installed over an insulation assembly that complies with the latest energy code requirements.



MECHANICALLY ATTACHED SINGLE-PLY SYSTEMS

Each TRI-BUILT® HD ISO panel should be secured as a coverboard over either an existing roof system or base layers of insulation. Butt edges and stagger joints of adjacent panels. Install the roof cover according to the manufacturer's specifications.

BUR & MODIFIED BITUMEN SYSTEMS (APP/SBS)

Each TRI-BUILT® HD ISO panel should be secured as a coverboard over either an existing roof system or base layers of insulation. TRI-BUILT® HD ISO may be adhered to a prepared concrete deck or subsequent layers of insulation with a insulation adhesive or cold applied mastic. Butt edges and stagger joints of adjacent panels. Install the roof cover according to the manufacturer's specifications.

PANEL CHARACTERISTICS

Manufactured using premium performance coated glass facer with white on one side of the board and dark on the other side, allowing the installer to choose which side to install up to control flash-off times in fully adhered applications. For all other applications the facer performance is unchanged.

- Contains no CFCs, HFCs, HCFCs
- 4 lbs/pcf high density foam core provides enhanced physical properties
- Lightweight (11 lbs per 4' x 8' panel); easy to cut, handle and install
- Sturdy constitution and durability protect the roof system from effects of hail, roof top construction traffic and other potentially damaging elements
- Available in 12" 4' x 8' (1220mm x 2440mm) and 4' x 4' (1220mm x 1220mm) panels

TRI-BUILT® HD ISO

TRI-BUILT® HD ISO THERMAL VALUES

Tested in accordance with ASTM C518

Thickness (inches)	Thickness (mm)	R-Value
0.5	13	2.5

POTENTIAL LEED CREDITS

- Energy and Atmosphere
- Optimize Energy Performance
- Materials & Resources
- Building Life-Cycle Impact Reduction
- Environment Product Declaration
- Material Reuse
- Pre-consumer Recycled Content
- Construction and Demolition Waste Management
- Indoor Environmental Quality
- Thermal Comfort

CODES AND COMPLIANCES

Achieves a UL 790 Class A combustible deck assembly rating at 12" thickness without the use of a fire-rated slip sheet or the presence of a fire barrier. Insulation joints must be staggered a minimum of 12" from the combustible deck joints. Maximum roof slope = 1:12

- Passed (10) ASTM D 3273 Resistance to Mold Test
- Hail Rating: SH-1
- ASTM C 1289 Type II, Class 4, Grade 1 (109 psi max)
- UL Classified 790
- UL Class A
- ASTM E 108
- FM Approved
- FM Approved 1-75
- Miami Dade County Product Control Approved
- State of Florida Product Approval No. FL 5968
- California Code of Regulations, Title 24, Insulation Quality
- Standard License #TI-1420

UL CLASSIFIED FOR USE IN CANADA

- Refer to UL Directory of Products Certified for Canada for more details
- UL Certified for Canada, CAN/ULC-S126, CAN/ULC- S107
- CAN/ULC-S704 Type 3 Class 2

TYPICAL PHYSICAL PROPERTY DATA

Per ASTM C 1289 – Polyiso Foam Core Only

Physical Property	Test Method	Value
Compressive Strength	ASTM D 1621	Grade 1 (109 psi max)
Dimensional Stability	ASTM D 2126	<0.5% linear change (7 days)
Water Absorption	ASTM C 209	<1% volume
Flame Spread*	ASTM E 84	< 75
Smoke Developed*	ASTM E 84	< 450
Service Temperature	–	260°F or less
Recycle Content		9% pre-consumer

*Meets the requirements of the IBC code. For specific Flame Spread or Smoke Developed Ratings please contact TRI-BUILT

WARNINGS AND LIMITATIONS

Insulation must be protected from open flames and kept dry at all times. Store above ground on pallets and cover with breathable tarpaulins. Installing only as much Polyiso as can be covered the same day with the completed roofing system. Do not leave exposed.

TRI-BUILT will not be responsible for specific designs by others, for deficiencies in construction or workmanship, for dangerous conditions on the job site or for improper storage and handling.

